

Ecomaxx Wet LimeMortar SuperFine

Version: v02 September 2024

Ecomaxx Wet LimeMortar SuperFine is a superfine natural lime-based mortar. It is formulated for interior applications only. It is applied as a final finishing coat for high-decoration finishes such as ironing, texturised, combed, etc. Ideal for plastering in building, rehabilitation and restoration of Heritage Buildings and Structures.

PRODUCT DESCRIPTION

Features:

Highly breathable.
Ultra-low VOCs emissions
Free of formaldehyde emissions.
Excellent adhesion.
Tough and long-lasting.
Good workability.
Absorbs CO₂.
Suitable for interiors only.

Physical and Technical Properties

Nature	- Hydrated lime, polymeric additives and calcium carbonate aggregates. Contain no acrylic or latex.
Colour	- Off-white
Working thickness	- Up to 1 mm per layer
Yield on level substrate	- Approximately 1.0 kg/m ² for 1 mm thickness (Depends on type and condition of substrate)
Pot life	- As long as pail is sealed with no water loss.
Setting time	- 2 to 3 hours (Depends on condition of substrate and weather)
Curing time	- 24 to 48 hours (Depends on condition of substrate and weather)
Adhesive Strength	- ≥ 0.5 N/mm ²

Format:

In plastic pail of 30 kg. It is supplied as a ready-to-use without addition of water.

Storage:

Keep in original pack, closed and in a cool and dry place. Keep from freezing and avoid direct sun exposure. Unopened, it may be conserved for at least 12 months from the date of manufacture.

APPLICATION INSTRUCTION

Application surfaces:

It can be applied on all types of common surfaces in construction: brick, concrete, masonry, etc.

Conditions of the substrates:

The substrate must be dry, firm, well adhered, free of any impurity and must have a grip to ensure the adhesion of the product.

Preparation of the substrates:

If the substrate presents algae, mould, fungi and / or other impurities, it is recommended to do a thorough cleaning, eliminating in its entirety and with specific products for this purpose.

If the substrate has poor adhesion, brush and apply *Graphenstone Minerseal Premium* diluted 3:1 with water.

If the substrate has salt deposits, brush and apply *Graphenstone Neutralysal Premium*.

On substrates without porosity, apply *Graphenstone Contak Premium*.

TECHNICAL DATA SHEET

Product preparation:

No preparation required as it is in ready-to-use paste form.

In very humid or highly contaminated areas, *Graphenstone Hydrox Seal Premium* is recommended to minimize water absorption.

Application method:

Apply a first level coat and then apply a second one evenly until achieving the desired thickness. At the start of drying, finish according to the desired finish.

The parts that are not going to be treated must be protected (glass, wood, etc.).

Do not mix with other products or specific properties may change.

If there are supports of different nature, meshes must be used.

Complementary products:

Graphenstone® products are recommended for the preparation of the substrate and protection of the finish. Refer to the relevant Technical Data Sheets.

Drying:

In conditions of 25 °C and 60% relative humidity: 24-48 hours between layers of mortar, 24 hours for its protection or at least 4 days for *Graphenstone®* painting. The carbonation process mainly occurs during the first 30 days.

ADDITIONAL INFORMATION

Usage warnings:

None in particular for normal use and people who do not have special pathologies. Protect skin and eyes especially. Apply with good ventilation, do not inhale product. Keep out of reach of children.

Tools:

Application: masonry brush, trowel, double-mix projecting machine, level.

Finishing: notched trowel or similar, sponge trowel.

Waste management:

According to local legal provisions. The packages are made of recycled polypropylene. Help protect the environment, do not throw waste through the drain and use the nearest recycling centre.

Tool cleaning:

Clean tools after use with warm water.

Notes:

Do not water for hardening, it hardens by absorbing atmospheric CO₂.

Do not apply to surfaces in constant contact with water.

It is recommended to protect the treated surface from rain for at least 4 days.

If not being painted it is recommended to consolidate and protect with *Graphenstone Minerseal Premium*.

Safety information:

For information regarding safety, physical, ecological and toxicological information see the latest version of the product's Material Safety Data Sheet.

Technical support:

For further information, please contact with local distributor or manufacture: info@graphenstonefareast.com